

**This Page Is Inserted by IFW Operations
and is not a part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- **BLACK BORDERS**
- **TEXT CUT OFF AT TOP, BOTTOM OR SIDES**
- **FADED TEXT**
- **ILLEGIBLE TEXT**
- **SKEWED/SLANTED IMAGES**
- **COLORED PHOTOS**
- **BLACK OR VERY BLACK AND WHITE DARK PHOTOS**
- **GRAY SCALE DOCUMENTS**

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Amendments to the claims:

This listing of claims will replace, without prejudice, all previous versions and listings of claims in the application.

1. (Twice Amended) An improved saw blade comprising:
a blade portion having two opposed sides which define a blade width; and
a cutting edge formed on the blade portion, the cutting edge having a cutting tip width;

the blade portion having a high precision surface finish which is less than or equal to approximately 10 Ra, and wherein the surface has reduced residual tensile stress which -and-is produced obtainable by a process comprising the steps of

providing a high speed centrifugal finishing apparatus having an outer vessel and at least one inner vessel;

placing the saw blade in the inner vessel;

adding abrasive finishing media into the inner vessel; and

rotating the inner vessel at high speed relative to the outer vessel; the high speed rotation causing the abrasive media to surface finish the blades.

2. (Original) An improved saw blade according to claim 1 wherein the saw blade is a straight saw blade and wherein the width of the blade portion is substantially the same as the width of the cutting tip.

3. (Original) An improved saw blade according to claim 1 wherein the saw blade includes an anti-kickback portion located circumferentially behind each cutting tip, and wherein the side surfaces of the anti-kickback portion are finished with a low friction surface.

4. (Original) An improved saw blade according to claim 1 wherein the high precision surface finish is in a range of between approximately 2 Ra and 6 Ra.

5. (Original) An improved saw blade according to claim 1 wherein the high precision surface finish is in a range of between approximately 2 Ra and 4 Ra.

6. (Original) An improved saw blade according to claim 1 wherein the high precision surface finish is approximately 6 Ra or less.

7. (Withdrawn)

8. (Withdrawn)

9. (Withdrawn)

10. (Withdrawn)

11. (Withdrawn)

12. (Withdrawn)

13. (Twice amended) An improved saw blade comprising:

a blade portion having two opposed sides which define the blade portion width;

and

a plurality of teeth formed on the blade portion, the teeth having opposed sides, the teeth having cutting tips formed thereon which have a width, the sides of the teeth having a high precision surface finish which is less than or equal to approximately 10 Ra, and wherein the surface has reduced residual tensile stress which is -and is-obtained obtainable-by a process comprising the steps of

providing a high speed centrifugal finishing apparatus having an outer vessel and at least one inner vessel;

placing the saw blade in the inner vessel;

adding abrasive finishing media into the inner vessel; and

rotating the inner vessel at high speed relative to the outer vessel; the high speed rotation causing the abrasive media to surface finish the blades.

14. (Original) An improved saw blade according to claim 13 wherein the saw blade is a straight saw blade and wherein the width of the blade portion is substantially the same as the width of the cutting tips.

15. (Original) An improved saw blade according to claim 13 wherein the saw blade includes an anti-kickback portion located circumferentially behind each cutting tip, and

wherein at least a portion of the anti-kickback portion have a high precision low friction surface finish.

16. (Original) An improved saw blade according to claim 13 wherein the high precision surface finish is in a range of between approximately 2 Ra and 6 Ra.

17. (Original) An improved saw blade according to claim 13 wherein the high precision surface finish is in a range of between approximately 2 Ra and 4 Ra.

18. (Original) An improved saw blade according to claim 13 wherein the high precision surface finish is approximately 6 Ra or less.

19. (New) An improved saw blade comprising:
a blade portion having two opposed sides which define the blade portion width;
and

a plurality of teeth formed on the blade portion, the teeth having opposed sides, the teeth having cutting tips attached to the teeth which have a width, the sides of the teeth having a high precision surface finish which is less than or equal to approximately 10 Ra, and wherein the surface is formed with a compressive residual stress through a process comprising the steps of

providing a high speed centrifugal finishing apparatus having an outer vessel and at least one inner vessel;

placing the saw blade in the inner vessel;

adding abrasive finishing media into the inner vessel; and

rotating the inner vessel at high speed relative to the outer vessel; the high speed rotation causing the abrasive media to surface finish the blades.